

# CC-601ABM

## Solvent-free epoxy floor mortar middle paint



ITLS INTERNATIONAL DEVELOPMENT

Sheet 1 of 1

### CHARACTERISTIC

- ◆ Solvent-free, no fire peril, no air pollution
- ◆ High corrosion and chemical resistance
- ◆ Low viscosity and easy applied
- ◆ High hardness and excellent abrasion resistance
- ◆ Seamless, non-cracking
- ◆ Easy to combine with silica sand

### APPLICATION

- ◆ Concrete coating
- ◆ Waste water treatment pool, pipeline coating
- ◆ Hospitals, electronic plants, textile, car repair plant

### PHYSICAL PROPERTIES

Color	Light brown, grey, green, black
Solid Content	> 90% (mix paint)
Viscosity	75-95 KU (25°C ,mix paint)
Composition	Above 98% (admix paint)
Pot life	Around 60 mins (25°C, admix paint)
Curing Time	Light Traffic : 24 hours Heavy Traffic : 48 hours Final Cured : 7 days
Packaging	A:20kg ; B:10kg
Quantity in theory	1.4-1.5kg/m <sup>2</sup> (Film thickness 1mm)
Stability	1 year
Operating condition	Trowel 、 roller and brush

### NOTICE

1. Main solvate and hardener have to mixing in electric mixer
2. Well mixing A and B then additive quartz gravel if want to additive mortar
3. Surface have to keep clean
4. Do not operation when temp is under 10°C